

CEMPOOL CIMENTART

TECHNICAL DATA

Coating without joints for interior swimming pools.

Finished thickness from 2 to 4 mm.

High resistance under water.

High resistance to chemical products.

Excellent adhesion on any support.

4 components

Rustic sand effect finish

Turquoise green waters

Indoor and outdoor

CIMENTART®
MICROCEMENT



PYME INNOVADORA

Válido hasta el 21 de julio de 2025



Commitment to the environment

CimentArt Microcement S.L.
Teléf: +34 965 654 637

Avda. Carrer la Mar, 12 - CP: 03560
www.grupocimentart.com

El Campello (Alicante)
info@grupocimentart.com



CEMPOOL CIMENTART - DATOS Y FICHA TÉCNICA

CEMPOOL CIMENTART is a continuous material without joints, ideal for coating the interior of swimming pools, whether they are newly built or renovated old pools. With the application of this product, you will achieve a unique sensation due to its sand color and will create a spectacular turquoise green effect in the water.

CEMPOOL CIMENTART is a thin, 4-component, solvent-free epoxy mortar.

This mixture contains waterproof additives that give our coating an excellent hardness. It is completely waterproof under both direct and indirect water pressure and has a high resistance to moisture and chemicals.

CEMPOOL CIMENTART can be applied on walls, stairs and floors in interior of swimming pools.

It can be applied inside tanks, ponds, fountains or water channels. It can be applied on all types of surfaces such as concrete, cement, gresite and tiles.

It can be applied even with a certain degree of humidity in the support (humidity of the concrete <6 %). Its application on ground floors or terraces is ideal to cut capillary humidity coming from the subsoil, for later finishing with ceramic tiles, wood or microcement.

ADVANTAGES

- Unique pools. Turquoise green watercolor.
- Possibility of finishing the pool, regardless of its size in 1 day.
- Great resistance to chemical products (chlorine, salt, etc.).
- Easier cleaning of algae and organisms as there are no joints.
- Maintenance free.

CEMPOOL CIMENTART - DATOS Y FICHA TÉCNICA

INDICATIONS

CEMPOOL CIMENTART is indicated:

- As a capillary moisture blocker or capillary moisture soils.
- For filling fissures or cracks.
- For repairing cracks that cause water loss in swimming pools.
- As interior coating in swimming pools.

PREPARATION OF THE SURFACES

The surfaces must be resistant and stable and must be clean and free of dust, grease, paint or in bad condition, lime, earth, badly glued tiles, loose tiles and any material that hinders its adherence.

Chipped paint or old chlorinated rubber in bad condition must be completely removed before the application of **CEMPOOL CIMENTART**.

The application of **CEMPOOL CIMENTART** will be carried out in a thin layer of 2 to 3 mm, so the supports where **CEMPOOL CIMENTART** will be applied must not have large areas with cracks, holes, missing tiles or gresites, etc.

You must first fill these areas with **CEMPOOL CIMENTART** and wait for it to dry completely before applying the final coat.

The tile joints in swimming pools must be perfectly filled and must not have any cracks. If you need to grout the pool you can use **CEMPOOL CIMENTART** and you do not need to clean the tile when you apply it.



CEMPOOL CIMENTART - DATOS Y FICHA TÉCNICA

CEMPOOL CIMENTART MIXING INSTRUCTIONS

Pour Component A, Component B and Component C into the empty bucket provided for mixing.

Mix the three components by mechanical means until a perfect homogeneous mixture is obtained and a homogeneous cream color is obtained.

Over the previous mixture of A+B+C, pour the content of Component D (powder) little by little and mix it by mechanical means until you have a homogeneous mixture without lumps.

APPLICATION INSTRUCTIONS

Start applying the first layer of **CEMPOOL CIMENTART** in sections with a steel trowel, in an orderly manner, in layers of 2 to 3 mm, making sure to cover all the joints of the tile and/or completely cover the entire surface.

CEMPOOL CIMENTART should be applied in a single layer. It is therefore important to leave the entire surface well covered so that the bottom is not visible and the tile joints are not noticeable.

Maximum during the following 10 minutes after having applied the layer of **CEMPOOL CIMENTART** (while the layer is still fresh, without drying) apply **ANTILEAK CIMENTART** with a short nap roller. This application is made over the entire applied surface, exerting a little pressure with the wet roller and going over the entire application to remove trowel marks and imperfections until a smooth cement finish is achieved.

Dampen the roller as many times as necessary with **ANTILEAK CIMENTART** when you notice that the roller is drier or **CEMPOOL CIMENTART** sticks to the roller. In areas where the roller cannot work, smooth **ANTILEAK CIMENTART** with the help of a sponge.

The application of **ANTILEAK CIMENTART** should always be done when **CEMPOOL CIMENTART** is fresh (just applied a few minutes after its application).



CEMPOOL CIMENTART - DATOS Y FICHA TÉCNICA

If too much time has passed since its application, the roller will not smooth. In any case, the roller must never be too dry, it must always be well soaked in **ANTI LEAK CIMENTART** to perform the application.

ANTILEAK CIMENTART is a product that is supplied ready to use, it is not advisable to dissolve it with any product, as it would lose its properties.

*If you wish to apply the product in 2 layers, you can also do it. Apply each layer with a minimum thickness of 2 mm and an interval of 24 hours between coats.

COVERAGE

As a jointing material: The approximate Yield per layer is $\pm 1 \text{ kg} / 1 \text{ m}^2 / \text{layer of } \pm 0.5 \text{ mm}$.

As an applied finishing material: The approximate Yield per layer is $\pm 5 \text{ kg} / 1 \text{ m}^2 / \pm 2/3 \text{ mm}$ layer.

PACKAGING FORMAT

15 kg Kits.

STORAGE

24 months, in a dry places protected from outdoor climate, the product been on the hermetically closed container.

CEMPOOL CIMENTART - DATOS Y FICHA TÉCNICA

TECHNICAL DATA

Presentation	Comp A: yellow viscous liquid Comp B: clear viscous liquid Comp C: transparent liquid Comp D: waterproof powder aggregate
Wear resistance BCA UNE-EN 13892-4:2003	20 µm
Density	1,9 kg/lt
Mixture Color	Sand beige
Adhesion resistance UNE-EN 13892-8:2003	3,6 N/mm2
Resistance to chemical agents, UNE-EN 13529	Chlorinated water: no change*
Resistance to chemical agents, UNE-EN 13529	Salt water: no change*
Impact resistance UNE-EN ISO 6272-1:2012	>14,7 Nm At 1500 mm impact without defects
Determination of surface hardness UNE-EN 13892-6	81 N/mm2
Water penetration under direct pressure 5 bar UNE-EN 12390	0 mm (No water penetration)
Water penetration under indirect pressure 5 bar UNE-EN 12390	No appearance of humidity or water on the surface
Slipperiness for traffic UNE 41901 EX	C3
Reaction to fire	Bfl S1
Life time of the mixture	Approx. 20 minutes, depending on ambient conditions
Accessibility	10 hours
Soaking or filling of the swimming pool	5 days after completion of application
Coverage	1.2 kg/ m2 / mm thickness
Packaging format 15 kg kits	Comp A: 4.40 kg Comp B: 990 gr Comp C: 500 gr Comp D: 9.1 kg
Transportation	Material considered non-hazardous
Expiration	24 months from date of manufacture
Storage	Dry and ventilated places, keeping the original containers closed.

*According to tests carried out in an approved laboratory on water with PH 7.2 and 0.2 gr of chlorine per 1000 lt of water and on salt water with PH 7.2, with 4 kg of salt per 1000 lt. Stronger concentrations of chlorine, bromine, magnesium, acids, flocculants and other chemicals may affect the finish, stability or shade of the material.

CEMPOOL CIMENTART - DATOS Y FICHA TÉCNICA

PRECAUTIONS BEFORE STARTING CEMPOOL CIMENTART APPLICATION

Do not apply with risk of freezing or if there is risk of rain during the application or in the following 4 days.

Do not apply at temperatures below 5°C or above 35°C.

The surfaces must be resistant and stable and must be clean and free of dust, grease, paint in poor condition, lime, dirt, poorly glued tiles, loose tiles and any material that hinders its adhesion. The Gresite (glass mosaic) pools must be perfectly joined.

There is a possibility that, with the passage of time, due to the action of chlorine, changes in the pH of the water, salt, lime and in general due to the contact of **CEMPOOL CIMENTART** with chemical products and the sun, a visible discoloration may occur in the waterline of the water. To avoid this, you can place stone or ceramic tiles on the waterline of the pool.

PRECAUTIONS DURING CEMPOOL CIMENTART APPLICATION

You must protect with tape squimmers, water impellers, drains, etc. and you have to remove the tape when the product is still fresh. Never leave the tape in place and allow the product to dry completely.

Mix Component A + B + C and then add Component D (powder) little by little, never add Component D all at once and then try to mix. Mix the 4 components without leaving too much time between them.

The mixer you use for mixing should be industrial or professional. Do-it-yourself drilling machines are not suitable for mixing.

It is recommended always and in any case (application in swimming pools or pavements) and whenever possible, that the complete application is done in the same day, so that no joints or splices are noticed.



CEMPOOL CIMENTART - DATOS Y FICHA TÉCNICA

Several people should do the **CEMPOOL CIMENTART** application. A minimum of 3 people is recommended for an application of approximately 50 m².

The useful life of the mixture once it has been applied is approximately 20 minutes. Once the **CEMPOOL CIMENTART** mixture begins to harden in the container, do not continue with its application, since the product will not have the same adherence.

Avoid applying **CEMPOOL CIMENTART** in situations of extreme heat or strong direct sunlight. Temperatures above 30°C will greatly accelerate drying.

The applied coats should be started and finished without stopping. Never leave a coat in the middle, once started, continue until its completion without stops, so that no cuts, joints or seams are noticed.

The purpose of applying **ANTILEAK CIMENTART** is to smooth and remove trowel marks and imperfections so that a smooth mortar is left. It is not intended to make an ultra fine finish with the application of this product.

ANTILEAK CIMENTART should always be applied when **CEMPOOL CIMENTART** is fresh (just applied within a few minutes of application). If too much time has passed since its application, the roller will not smooth. In any case, the roller must never be too dry, it must always be soaked with **ANTILEAK CIMENTART** to perform the application. In the case of applying the roller in some areas soaked and in other areas very dry, it may cause visible roller marks and slight color changes.

During the application, avoid air currents that can bring dust, leaves or any type of dirt, since they may cause them to adhere to the product.

PRECAUTIONS AFTER THE APPLICATION OF CEMPOOL CIMENTART

You need 5 days to fill the pool or wet the surface. Never do it before 5 days.

CEMPOOL CIMENTART - DATOS Y FICHA TÉCNICA

1 day after the pool is completely filled with water, add the water maintenance product. Under no circumstances add the water maintenance product while the pool is being filled.

Subsequently, never add any water maintenance or treatment product (chlorine, bromine, salt, maintenance products, flocculants, etc.) directly, without first diluting it with water. We recommend that you read the manufacturer's exact instructions and do not add more than the amount needed. This may affect the final finish and discoloration may occur.

Do not place chlorine tablets or salts directly on the pool floor or resting on the ladder floor. This may cause color changes. Chlorine tablets should be placed in the pool squimmer.

Any liquid or granular product should be diluted with water and poured into the squimmer with the pool filtering system running and the selector valve in the re-circulation or filtration position.

We recommend maintaining a pH of 7.2 in the water.

Use the appropriate PPE (EPIs), such as clothing, gloves and mask to apply the products. The tools and working tools are cleaned with universal solvent.

CIMENTART MICROCEMENT SL. Our systems are based on the research carried out in our laboratories and years of practical experience.

We guarantee that our products are manufactured, packaged and labeled under the guidelines of ISO 9001: 2008.

We decline any responsibility if the result is affected by factors beyond our control.

The end user must verify that the product supplied meets the needs for which it is going to be used, and must carry out a preliminary test in each case that is necessary.

Revision date: 10-08-21.

The present edition of this technical sheet cancels the previous ones.

