

# New WB Bi- COMPONENT POLYURETHANE CIMENTART 2022

## TECHNICAL DATA SHEET

Transparent coating odorless  
of high resistance that can be  
used in interior and exterior

Great cohesion over any  
cement, wood or painted surface

Complete waterproofing

High resistance to abrasion  
and sun light UV rays

Anti-slip and anti-bacteria  
Prevents the bacteria growth  
and formation of fungi

3 perfect finishing:  
GLOSS, MATE AND SATIN

Easy application, bubbles free

Use in interior and  
exteriors walls and floors

Faster drying, two coats  
can be applied on the same  
day

**CIMENTART®**  
MICROCEMENT



**PYME INNOVADORA**  
Válido hasta el 16 de noviembre de 2020



**Commitment with the environment**

CimentArt Microcement S.L.  
Teléf: +34 965 654 637

C/ Dr Pedro Herrero, nº 5 - CP: 03550  
www.grupocimentart.com

San Juan de Alicante (Alicante)  
info@grupocimentart.com



## CIMENTART WB Bi-COMPONENT POLYURETHANE – TECHNICAL DATA SHEET

The **CIMENTART WB Bi-COMPONENT POLYURETHANE** is a waterproofing coating, made of aliphatic polyurethanes, of high resistance to washing and weathering (Comp A) and an aliphatic isocyanate without solvents (Comp B), recommended to be used over the Microcement coatings, concrete, printed concrete, polished cement and wood.

With the application of the **CIMENTART WB Bi-COMPONENT POLYURETHANE**, you achieve:

- Protection of the microcement coating, cement and wood.
- Enhancement of its aesthetic finishing.
- Three different finishing: gloss, satin and mate.
- Increased resistance to abrasion.
- Complete waterproofing of the surface.
- It allows to clean the surface where is applied, with any type of chemical product.
- Resistant to chlorhydric acid.

### TECHNICAL DATA COMPONENTE A + B

	<b>A COMPONENT</b>	<b>B COMPONENTE</b>
<b>Type</b>	<b>High resistance polyurethane resins</b>	<b>Aliphatic isocyanate without solvent</b>
<b>Color</b>	<b>White. When dry is transparent</b>	<b>Transparent</b>
<b>Appearance</b>	<b>Liquid</b>	<b>Liquid</b>
<b>Viscosity</b>	<b>sp-2, 1.5 rpm, 1.000 cps</b>	<b>sp-1, 12 rpm, 12.5 cps</b>
<b>Specific weight at 20 °C</b>	<b>40%</b>	<b>50%</b>
<b>Packaging 1, 5 and 25 kg.</b>	<b>1 kg: 714.30 gr comp A. 5 kg: 3.57 kg comp A. 25 kg: 17.85 kg comp A.</b>	<b>285.70 gr comp B. 1.43 kg comp B. 7.15 kg comp B.</b>

## CIMENTART WB Bi-COMPONENT POLYURETHANE – TECHNICAL DATA SHEET

### TECHNICAL DATA OF THE A + B MIX

<b>Mix proportion</b>	<b>5 parts Comp A / 2 part Comp B</b>
<b>Color</b>	<b>White. When dry is transparent</b>
<b>Appearance</b>	<b>White liquid</b>
<b>Mix duration at 20 °C</b>	<b>1 hour</b>
<b>Viscosity Brookfield LTV</b>	<b>20°C sp-2 1,5 6 rpm:4000 cps</b>
<b>Density at 20 °C</b>	<b>1.3 gr/cc ± 2%.</b>
<b>Application temperature</b>	<b>+ 5°C / + 30°C</b>
<b>Degree of gloss</b>	<b>Gloss: 8 - 12 hours Satin: 6 -10 hours Matt: 4 – 8 hours</b>
<b>Drying time</b>	<b>3 hours</b>
<b>Maximum repaint time</b>	<b>8 hours</b>
<b>Finishing after hardening</b>	<b>Gloss, Satin or Matt</b>
<b>Hardness Konig (3 días):</b>	<b>95-100 seg (ISO 1522:2006)</b>
<b>Slippery</b>	<b>UNE EN 13036-4 PTV 100</b>
<b>Friction</b>	<b>UNE EN 14904:2007</b>
<b>Fire resistance</b>	<b>Not flammable - Euro class BFL S1</b>
<b>Abrasión resistance</b>	<b>50 mg (CS-10, 1Kg, 1.000 cycles) EN-ISO 5470-1.</b>
<b>Impact resistance</b>	<b>III Class EN ISO 6272-1</b>
<b>Shipping</b>	<b>Material not dangerous</b>
<b>Storing</b>	<b>Material not dangerous</b>

VOCs content max: 125 g/l. \*EU limit value of the product (cat.A/J):140 g/l (2010).

### USE INSTRUCTIONS

In absorbing surfaces, apply previously a layer of **CIMENTART Sealer**.

Mix the two components, using an electric mixer, until you get a perfect homogeneous mixture. Is done using the following proportions: 5 parts of Polyurethane (component A) to 2 part of Hardener (component B). It is important to mix completely the two components to avoid the appearance of areas of different grades of gloss due to a deficient dispersion of the two components.

## CIMENTART WB BI-COMPONENT POLYURETHANE – TECHNICAL DATA SHEET

---

To achieve an extra hardness and resistance to scratching, especially on pavements with heavy traffic of people or greater wear, you can make the mixture in the following proportions: 5 parts of Polyurethane (component A) for 2 part of Hardener (component B).

After the correct mixing is done you should filter the mixing using a metallic strainer.

Once the mixing is filtered if you notice the formation of small bubbles, you should wait 5 minutes before you start the application.

Apply one layer, in an orderly way without stretching too much the product, ensuring that no area is left uncovered, and without excesses, creating a layer of the thickness of a paper sheet. Cover very well all the areas with water contact and the joints where the water can penetrate.

In vertical areas make sure that the product doesn't create drops that slide down. Use the roller to fix the situation.

A too thick layer can produce:

- The products drops (in walls).
- A too slow drying.
- Decreased hardness due to excess of product. Remember that the recommended amount of product (once soaked in the roller), by m<sup>2</sup> is 60 to 80 g.

Drying time: Before applying the second layer of **CIMENTART WB BI-COMPONENT POLYURETHANE**, make sure that the first layer is completely dry, approximately 3 to 4 hours, depending on the ventilation and temperature of the room.

Repainting time for the second layer: it must be repainted before 8 hours, since after this time blistering and/or lack of adherence of the second layer may occur. After this time (8 hours) it is essential to sand between layers.

**This product needs good ventilation in the room where it is applied.**

The life span of the product once mixed is about 1 hour, after that you will notice an increased viscosity and the hardener properties will be lost. Is recommended to use the mixed product in less than 1 hour.

## CIMENTART WB BI-COMPONENT POLYURETHANE – TECHNICAL DATA SHEET

---

The drying time before use the surface is minimum 72 hours. The minimum time of wait before put the surface in contact with water is 1 week.

The product is presented ready to use, we do not advise its dilution, which would cause loss of properties of hardness and waterproofing.

Apply directly with a varnish roller, a brush or an airless system over a dust free surface. We recommend brushing the surface after apply the product to remove possible air bubbles, especially on very hot, dry and highly ventilated site.

Clean all tools with water.

### DRYING TIMES

The drying of the **CIMENTART WB BI-COMPONENT POLYURETHANE** depends on the temperature, ventilation and humidity. Normally it will be completely dry between 3 to 5 hours, depending on the ventilation and temperature of the room.

### ULTRA VIOLET RAY RESISTANCE

**CIMENTART WB BI-COMPONENT POLYURETHANE** is an aliphatic product. It is completely resistant to the action of UV rays and does not yellow to the outside.

## CIMENTART WB Bi-COMPONENT POLYURETHANE – TECHNICAL DATA SHEET

### RESISTANCE TO CHEMICAL PRODUCTS ONCE APPLIED

PRODUCT	RESISTANCE 24 h	RESISTANCE 10 DAYS
Water	10	10
Thinner	0	4
Alcohol	0	4
Ammonia	0	7
Hydrochloric acid	5	9
Peroxide	0	3
Pure bleach	5	8
Hairdressing dyes	0	1
Acetone	0	0
Gasoline	2	7
Hot cooking oil	4	10
Coffee	8	10
Wine	9	10
Lemon	6	10
Coca cola	7	10
Beer	10	10
*10 maximum score. 0 minimum score		

### EFFICIENCY

With 1 liter of **CIMENTART WB Bi-COMPONENT POLYURETHANE**, you can cover approximately 12 to 18 m<sup>2</sup> of surface, depending on the absorption of the support and the thickness of the applied layer.

We recommend 2 layers on surfaces with no contact with water and 3 layers on surfaces with contact with water or humidity (exterior surfaces, shower plates, WC or kitchen worktops, etc.)

### RECOMMENDED FINISHES

Floors: we recommend, without exception, that you apply on floors, interior and exterior, the **CIMENTART WB Bi-COMPONENT POLYURETHANE GLOSS**, for a better cleaning of the surface. The Mate floor many times gives to the customers the impression of being not-finished, old and dirty.

CimentArt Microcement S.L.  
Teléf: +34 965 654 637

C/ Dr Pedro Herrero, nº 5 - CP: 03550  
www.grupocimentart.com

San Juan de Alicante (Alicante)  
info@grupocimentart.com



## CIMENTART WB Bi-COMPONENT POLYURETHANE – TECHNICAL DATA SHEET

---

Walls: In walls, you can apply any of the 3 available finishes: Matt, Gloss or Satin, according to the customer choice.

### PACKAGING

The **CIMENTART WB Bi-COMPONENT POLYURETHANE** for all types of finishing: Glossy, Satin or Matte

Is available in 3 different recipients:

- 1 kg: Comp A: 714.30 gr. Comp B: 285.70 gr.
- 5 kg: Comp A: 3.57 kg. Comp B: 1.43 kg.
- 25 kg: Comp A: 17.85 kg. Comp B: 7.15 kg.

### STORING

12 months, in a dry place protected from bad weather, in original recipient hermetically closed.

### RECOMENDATIONS

Do not dilute the product with water or solvents.

Never apply the product on substrates that are wet, damp or have capillary moisture. Do not apply the product if there is a humidity in the environment of more than 50%.

Do not apply in layers greater than 0.1 mm. Respect the recommended drying times. A good ventilation is necessary in the rooms where it is applied.

Do not apply with risk of frost or rainy weather. Do not apply at temperatures below 5°C or above 35°C.



## CIMENTART WB Bi-COMPONENT POLYURETHANE – TECHNICAL DATA SHEET

---

Never leave any of the layers in half, once the application is started, continue until its completion without stopping, so you do not see cuts, encounters or joints. If the surface is very large, several people must make the application at the same time.

Protect furniture, chairs or tables with protective felts.

Never drag furniture or other objects and protect the pavement if you are going to carry out other construction work on the pavement.

Merchandise considered not dangerous in matters of transport. It is water based, free of solvents, alcohols or flammable products.

Use the appropriate PPE. Do not place children within reach, avoid contact with eyes and skin through appropriate PPE. In case of contact with the eyes, rinse thoroughly with water and consult your doctor in case of subsequent discomfort.

Once the application is finished, let it dry completely and let it run for at least 4 days before doing other types of work and 7 days before moistening or receiving water.

*CIMENTART MICROCEMENT SL. Our systems are based in the research done at our laboratories and the many years of practical experience we have.*

*We guarantee that our products are manufactured, packaged and labeled under the rules of Normative ISO 9001:2008.*

*We decline any responsibility if the end result is affected by external factors not under our control.*

*The end user must check that the product supplied is adequate to the needs that is going to be used for, doing a test in any case that must be necessary.*

*Review date: 04-10-22.*

*The present document cancels the earlier editions.*

